



RESINEX

Rotomoulding

Certificate Of Analysis

Material: RX 446 BLACK 9003 M834

Batch: 723266


Quantity: 4,218 Kg

Density: 0.950 g/cm³

MFI: 4.0 g/10min

Pallet Number	Bag Number	Sieve Size (μ)							Bulk Density	Dry Flow
		0	150	212	300	425	500	600		
AVERAGE (%)		7.7	9.3	21.1	25.5	17.1	17.6	1.7	39.7	22.7

Particle Size Distribution



The information provided in this documentation corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits nor used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Resinex cannot anticipate all variations in actual end-use conditions Resinex makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights.